CUTTING CONDITIONS

Milling | Endmills | Cutting conditions

NEO-CR-EMS

Side milling

	C≤0,2% - GG S55C · SS400 · FC250 ~750 N/mm²		SCM - SKD SKT · SKS · SCM ~30 N/mm²		30~38 HRC NAK55 · HPM1 · SKT · SKD 30~38 N/mm²		38~45 HRC - SUS SUS304 · SKD 38~45 N/mm²		45~55 HRC - HRS Titanium alloy 45~55 N/mm²		Heat resistant alloy steel Inconel	
Ø	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)
6	7,100	2,300	5,500	1,750	4,700	1,300	4,400	1,250	4,300	1,050	2,200	360
8	5,350	2,250	4,150	1,600	3,500	1,200	3,300	1,200	3,200	1,000	1,650	330
10	4,300	2,100	3,350	1,550	2,850	1,100	2,650	1,050	2,600	925	1,350	310
12	3,600	2,000	2,800	1,500	2,350	1,050	2,250	980	2,150	875	1,100	305
16	2,700	1,750	2,100	1,350	1,750	925	1,650	805	1,600	735	835	305
20	2,150	1,450	1,650	1,100	1,400	850	1,350	745	1,300	665	670	300

Max cutting depth



ap	ae
≤ 1,5 D	≤ 0,2 D

ap	ae
≤ 1,5 D	≤ 0,1 D

ap	ae
≤ 1,5 D	≤ 0,05 D

1. Use a rigid and precise machine and holder
2. Please adjust the speed and feed when the cutting depth is large or when machines with low rigidity are used
3. Please use a suitable fluid with high smoke retardant properties
4. During dry (no fluid) milling, please use air blow to remove disposable chips from the milling area and to eliminate chip packing

NEO-CR-EMS

High speed side milling

	C≤0,2% - GG S55C · SS400 · FC250 ~750 N/mm²		SCM - SKD SKT · SKS · SCM ~30 N/mm²		30~38 HRC NAK55 · HPM1 · SKT · SKD 30~38 N/mm²		38~45 HRC - SUS SUS304 · SKD 38~45 N/mm²		45~55 HRC - HRS Titanium alloy 45~55 N/mm²		Heat resistant alloy steel Inconel	
Ø	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)	S (min⁻¹)	F (mm/min)
6	14,000	4,750	11,000	3,550	9,150	2,650	8,600	2,500	8,350	2,100	4,300	745
8	10,500	4,600	8,050	3,300	6,850	2,450	6,450	2,400	6,250	2,050	3,250	675
10	8,400	3,900	6,500	3,000	5,550	2,200	5,200	2,100	5,050	1,900	2,600	640
12	7,000	3,800	5,450	2,900	4,600	2,150	4,350	2,000	4,200	1,800	2,150	625
16	5,250	3,550	4,100	2,800	3,450	1,900	3,250	1,650	3,150	1,500	1,650	620
20	4,200	2,900	3,250	2,250	2,750	1,750	2,600	1,550	2,550	1,350	1,300	610

Max cutting depth



ap	ae
≤ 1,5 D	≤ 0,05 D

ae max = 0,5mm

ap	ae
≤ 1,5 D	≤ 0,02 D

ap	ae
≤ 1 D	≤ 0,02 D

ae max = 0,5mm

1. Use a rigid and precise machine and holder
2. Please adjust the speed and feed when the cutting depth is large or when machines with low rigidity are used
3. Please use a suitable fluid with high smoke retardant properties
4. During dry (no fluid) milling, please use air blow to remove disposable chips from the milling area and to eliminate chip packing